

KEMPEROL Roofpatch

Uses

- For repairing leaks
- For flat and sloping surfaces

Features

- Water vapour permeable
- Crack bridging
- Fleece-reinforced
- Cold applied
- Solvent-free
- UV resistant
- single-component
- Based on: Silane-modified polymer

Pack sizes

41 x 27 cm in aluminium bags
5 pieces in a cardboard box

Shelf Life

Store unopened in a cool, dry, frost-free place. See label for use before date.

Properties

Colour	Pale grey
Workability time *	approx. 30 min
Rainproof after *	approx. 60 min
Can be walked on after *	approx. 12 h
Cured after*	approx. 1–2 d

* Values obtained at a temperature of 23 °C - 50% rel. humidity. These values vary depending on the weather conditions, such as wind, humidity and temperature.

Laying

Preparing the substrate

The substrate must be dry, sound and free from any material that would hinder adhesion.

Only apply when the substrate and ambient temperatures are $\geq +5$ °C.

On the following substrates the KEMPEROL rooftop patch can be applied without priming:

Surfaces	No priming
Standard bitumen sheets	+
PVC roof sheets	+
Concrete	+
Wood	+
Screed	+
Resin-modified screed	+
Metal	+

Place the aluminium bag on a flat surface and use the side of your hand to evenly distribute the material in the bag. Take out and put on the gloves attached to the bag. Open the bag at the provided tear aid, pull out the KEMPEROL rooftop patch and apply it to the area to be waterproofed. Smooth out any bubbles and creases. While still wet, the KEMPEROL rooftop patch can be scattered with slate chips to match the existing roof surface.

PPE

Personal protective equipment should be worn.

Important notice

The material safety data sheets, identification of the units, hazard warnings and safety recommendations on the units must be observed during transportation, storage and application.

The leaflets issued by the chemical industry's accident prevention and insurance association must be observed when the product is used.

Disposal

liquid	EAK 08 04 09
cured	EAK 08 04 10

General information

The times given are reduced and increased with higher and lower ambient and substrate temperatures respectively. KEMPER SYSTEM products must not be mixed with other manufacturers' products.

Only for commercial use.

Our technical data sheets / technical information and application instructions reflect the current level of knowledge in our company and the experience with our products. In each case, the new edition supersedes the previous technical information and renders it invalid. It is therefore necessary that you always have to hand the current code of practise. The latest version can be retrieved from the KEMPER SYSTEM Login section. When using our products, a detailed, object-related and qualified inspection is required in each individual case in order to determine whether the product and /or application technology in question meets the specific requirements and purposes. We are liable only for our products being free from faults, and this only if our relevant product has been used and applied according to the instructions in our technical data sheets. Correct application of our products therefore falls entirely within the scope of liability and responsibility of the user (contractor). Our products are sold exclusively on the bases of our conditions of sale and delivery.

Issued: Vellmar, 2018-12-12